

UirginiaTech. Transportation Institute









Effect of Traffic and Environmental Factors on Roughness Progression Rate of Sealed Low Volume Arterials

• Nahla Alaswadko (PhD Student)

TASSETS (ICMPA9)

Rayya Hassan

international Conference on

Robert Evans

Swinburne University of Technology

Outline

- Introduction
- Study Aim
- Network Selection Criteria
- Study Approach
- Models Development
- Models Validation
- Study Outcomes

Introduction

- Pavement management at network or project level is impossible without reliable accurate performance prediction models
- Requirements for more powerful models:
 - A representative network
 - An acceptable database
 - A wide range of factors
 - An appropriate preparation of data
 - A suitable functional form of the model
 - An assessment of the accuracy of predicted model

Study Aim

- The main purpose is to develop an empirical absolute deterministic roughness prediction models for managing low volume rural roads (class C) of Victoria's arterial network.
- Study the contribution and significance of relevant influencing factors in predicting roughness.



Network Selection Criteria

 (13) highway sections with a total length of 653 km (6,536 100msegments) were selected. Covering different types of:



Victoria's map and locations of selected road sections

NETWORK SELECTION CRITERIA

Pavement type for class C roads

- Two lane sealed type roads with shoulders.
- Provide important links between population centers, and between these centers and the primary transport network.





Cross section of unbound granular pavement with spray/chip seal

Study Approach

Data collection process

 Condition data

 Factors affecting pavement performance Data preparation process

- Alignment
- Filtering
- Screening
- Matching
- Arranging

Data splitting

- Model development
- Model validation

Analysis approach

- Absolute /aggregate deterministic approach
- Family group data fitting approach

Data Collection Process



- Condition data (DV)
- Roughness (IRI, m/km)



Factors affecting pavement roughness progression (IVs)

- Traffic loading
- Pavement strength
- Pavement age
- Subgrade soil
- Climate
 - Drainage
- Terrain

Data Preparation Process

| Alignment | Using profile viewing and analysis (ProVal)software Using In-house Excel-based tool |
|-----------|--|
| Screening | Using profile viewing and analysis (ProVal) software Using statistical package for social sciences (SPSS) |
| Filtering | • Using linear rate of progression (LRP) tool |
| Matching | • Using Excel software for matching chainage of all variables. |
| Arranging | Using Excel software for developing time series datasets |
| 6/4/2015 | 9th International Conference on Managing |

Pavement Assets | May 18-21, 2015

Data Splitting



9th International Conference on Managing Pavement Assets | May 18-21, 2015

Analysis Approach

 Multiple regression analysis was used to develop roughness models for the whole data set and relevant families/groups:

Roughness (IRI) = f (traffic loading, soil reactivity, climate, drainage and terrain)

- Traffic loading in million equivalent standard axles (MESA): ranged (0.032 to 2.495)
- Soil reactivity (SSR): coded (non- expansive=0 and expansive=1)
- Climate in terms of Thornthwaite Moisture Index (TMI) : ranged (-24 to 54)
- Drainage (DRA): coded (good = 0 and poor = 1)
- Terrain (TER): coded (flat = 0 and non- flat = 1)

Analysis Approach

The development of roughness includes three phases; initial, gradual and rapid deterioration. Only gradual phase was considered.



Models Development

Roughness Model (IRI, m/km)

Log IRI = 0.38 √MESA – 0.001 TMI + 0.255 SSR + 0.047 DRA + 0.018 TER

- No constant
- Gradual phase (IRI = 1.8 to 6.7 m/km)
- Time series sample size (N) = 8,971
- Std. Error of Est. = 0.143 m/km IRI
- Partial R^2 for MESA = 62%, SSR = 53%, TMI=1%, DRA=1.7% & TER=0.3%
- Higher traffic loading and soil reactivity, poor drainage, non-flat terrain and dry climate increase roughness progression rate.

Roughness Model (IRI, m/km)



Roughness Model (IRI, m/km)

Roughness model for expansive soil

Roughness model for non-expansive soil

Log IRI = 0.675 √MESA - 0.002 TMI + 0.067 DRA + 0.163 TER Log IRI = 0.42 √MESA + 0.004 TMI + 0.237 DRA

- Sample size (N) = 6,848
- Std. Error of Est. = 0.178 m/km IRI
- Partial R^2 for MESA = 81%, TMI=5%, DRA=3% & TER=10%

- Sample size (N) = 2,123
- Std. Error of Est. = 0.133 m/km IRI
- Partial R^2 for MESA = 90%, TMI=18% & DRA=31%

Roughness Model (IRI, m/km)



 Expansive soils are associated with higher roughness rate than non-expansive

9th International Conference on Managing Pavement Assets | May 18-21, 2015





Poor drainage produces higher roughness rate than good drainage





- Dry areas exhibit higher roughness rate than wet areas in expansive soil
- Wet areas exhibit higher roughness rate than dry areas in non-expansive soil

Model Validation

Validation of whole dataset model

72% of sample size (8,263) within residual value ± 1 IRI with std. dev. = 0.48



9th International Conference on Managing Pavement Assets | May 18-21, 2015

Conclusions

Main points of study outcomes are:

- Traffic loading and soil reactivity are the most important predictors of pavement roughness progression.
- Sections built on expansive subgrade soils are associated with higher roughness values and progression rates than those with non-expansive soils
 - Expansive soil is sensitive to moisture changes during seasonal variation cycles which leads to swelling or shrinkage phenomena.

Conclusions

- Sections in arid climates exhibit higher roughness progression than those in wet climates, regardless of the type of subgrade soil reactivity.
 - This is mainly due to the fact that the former experience higher seasonal moisture variation than the latter.
- Sections with expansive subgrade soils in arid climates exhibit higher roughness progression than those in wet climates.
- Sections with non-expansive subgrade soils in wet climate zones exhibit higher roughness progression than those in dry climate zones.



Any Questions

